Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 06/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	06/01/2020	149.89 X 151.24 X 149.47	22669	**8.870**	541.5	23.9	22.8
2	Roof Concrete	M25	30/12/2019	06/01/2020	149.78 X 150.13 X 151.56	22487	**8.089**	501.0	22.3	
3	Roof Concrete	M25	30/12/2019	06/01/2020	150.18 X 150.38 X 149.37	22583	**8.419**	500.5	22.2	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 27/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 27/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	27/01/2020	149.92 X 149.53 X 151.77	22418	**8.058**	608.3	27.1	27.3
2	Roof Concrete	M25	30/12/2019	27/01/2020	149.08 X 150.54 X 151.27	22443	**8.860**	602.2	26.8	
3	Roof Concrete	M25	30/12/2019	27/01/2020	151.54 X 150.04 X 151.96	22737	**8.483**	637.3	28.0	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 06/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	06/01/2020	151.87 X 151.62 X 151.93	23025	**8.870**	549.8	23.9	23.2
2	Roof Concrete	M25	30/12/2019	06/01/2020	149.96 X 149.29 X 151.66	22387	**8.089**	508.1	22.7	
3	Roof Concrete	M25	30/12/2019	06/01/2020	150.99 X 150.12 X 149.62	22667	**8.419**	519.3	22.9	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 27/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 27/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	27/01/2020	151.77 X 150.00 X 151.08	22766	**8.058**	627.1	27.5	27.5
2	Roof Concrete	M25	30/12/2019	27/01/2020	150.92 X 149.60 X 151.19	22577	**8.860**	606.2	26.9	
3	Roof Concrete	M25	30/12/2019	27/01/2020	150.93 X 150.27 X 151.65	22680	**8.483**	637.6	28.1	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro
Sig.
Date
BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 06/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	06/01/2020	149.56 X 149.10 X 149.97	22300	**8.870**	526.1	23.6	22.8
2	Roof Concrete	M25	30/12/2019	06/01/2020	151.38 X 149.75 X 149.40	22670	**8.089**	509.5	22.5	
3	Roof Concrete	M25	30/12/2019	06/01/2020	151.93 X 149.04 X 150.63	22644	**8.419**	508.9	22.5	

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 27/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 27/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	27/01/2020	151.90 X 150.82 X 150.80	22910	**8.058**	621.6	27.1	27.3
2	Roof Concrete	M25	30/12/2019	27/01/2020	151.21 X 151.92 X 151.79	22971	**8.860**	602.2	26.2	
3	Roof Concrete	M25	30/12/2019	27/01/2020	151.01 X 149.03 X 150.16	22505	**8.483**	641.2	28.5	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro
Sig.
Date
BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 06/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	06/01/2020	149.02 X 150.26 X 151.76	22392	8.870	526.8	23.5	22.6
2	Roof Concrete	M25	30/12/2019	06/01/2020	151.96 X 149.78 X 151.26	22761	8.089	505.3	22.2	
3	Roof Concrete	M25	30/12/2019	06/01/2020	150.87 X 149.94 X 151.13	22622	8.419	499.4	22.1	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 27/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 27/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	27/01/2020	149.13 X 150.94 X 151.93	22509	**8.058**	618.5	27.5	27.3
2	Roof Concrete	M25	30/12/2019	27/01/2020	149.41 X 149.02 X 149.21	22265	**8.860**	582.6	26.2	
3	Roof Concrete	M25	30/12/2019	27/01/2020	150.65 X 151.54 X 151.67	22829	**8.483**	645.1	28.3	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65**

Date: 06/01/2020

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	06/01/2020	150.28 X 149.26 X 151.05	22431	**8.870**	532.7	23.7	22.9
2	Roof Concrete	M25	30/12/2019	06/01/2020	150.83 X 151.27 X 150.90	22816	**8.089**	512.5	22.5	
3	Roof Concrete	M25	30/12/2019	06/01/2020	150.55 X 150.67 X 150.40	22684	**8.419**	513.2	22.6	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 27/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 27/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	27/01/2020	149.76 X 150.05 X 150.84	22471	**8.058**	622.6	27.7	27.8
2	Roof Concrete	M25	30/12/2019	27/01/2020	150.70 X 150.76 X 151.43	22719	**8.860**	612.2	26.9	
3	Roof Concrete	M25	30/12/2019	27/01/2020	150.74 X 150.83 X 149.71	22737	**8.483**	651.7	28.7	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 06/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	06/01/2020	150.02 X 151.21 X 150.16	22685	**8.870**	543.9	24.0	23.1
2	Roof Concrete	M25	30/12/2019	06/01/2020	150.46 X 149.90 X 150.38	22553	**8.089**	509.0	22.6	
3	Roof Concrete	M25	30/12/2019	06/01/2020	150.28 X 151.49 X 150.44	22767	**8.419**	520.9	22.9	

Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro
Sig.
Date
BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 27/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 27/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	27/01/2020	149.59 X 151.58 X 149.44	22676	**8.058**	632.6	27.9	27.5
2	Roof Concrete	M25	30/12/2019	27/01/2020	149.57 X 151.54 X 151.18	22667	**8.860**	589.7	26.0	
3	Roof Concrete	M25	30/12/2019	27/01/2020	151.45 X 149.33 X 150.74	22615	**8.483**	643.7	28.5	

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 06/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	06/01/2020	151.31 X 150.15 X 150.29	22719	**8.870**	532.9	23.5	22.7
2	Roof Concrete	M25	30/12/2019	06/01/2020	150.92 X 149.39 X 150.02	22545	**8.089**	502.5	22.3	
3	Roof Concrete	M25	30/12/2019	06/01/2020	150.68 X 151.99 X 151.25	22902	**8.419**	513.4	22.4	

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 27/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 27/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	27/01/2020	149.57 X 149.08 X 149.03	22299	**8.058**	602.7	27.0	27.3
2	Roof Concrete	M25	30/12/2019	27/01/2020	150.65 X 151.25 X 149.50	22785	**8.860**	608.1	26.7	
3	Roof Concrete	M25	30/12/2019	27/01/2020	151.17 X 149.22 X 150.30	22557	**8.483**	634.9	28.1	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 06/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 06/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	06/01/2020	151.91 X 149.02 X 149.70	22637	**8.870**	539.7	23.8	23.1
2	Roof Concrete	M25	30/12/2019	06/01/2020	150.60 X 150.39 X 149.08	22648	**8.089**	519.5	22.9	
3	Roof Concrete	M25	30/12/2019	06/01/2020	149.24 X 149.05 X 149.48	22244	**8.419**	501.6	22.5	

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-24-65** **Date: 27/01/2020**

Project Name : Construction of Hospital Building at Ward No.11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.C.N.S Murthy #12, 3rd Cross, S.V.G.N.S.S Layout, 3rd Stage, 4th Block, Basaveshwaranagara, Bangalore-560079

Customer's Reference : EE(Project)/Ynk Zone/WO/16/18-19

Date of Receipt : 01-01-20

Customer ID : Roof Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 27/01/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Roof Concrete	M25	30/12/2019	27/01/2020	150.47 X 150.99 X 149.73	22719	**8.058**	634.1	27.9	27.5
2	Roof Concrete	M25	30/12/2019	27/01/2020	151.37 X 149.98 X 151.38	22702	**8.860**	602.4	26.5	
3	Roof Concrete	M25	30/12/2019	27/01/2020	149.50 X 150.92 X 151.11	22562	**8.483**	635.3	28.2	

Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com